

PAT-NO: JP406145049A  
DOCUMENT-IDENTIFIER: JP 06145049 A  
TITLE: CROSS-LINKING TYPE CATAPLASM BASE

PUBN-DATE: May 24, 1994

**INVENTOR-INFORMATION:**

NAME	COUNTRY
YAMAZAKI, KAZUO	
NAKAMURA, SUSUMU	
NARA, MASATO	
NEMOTO, MASAMI	

**ASSIGNEE-INFORMATION:**

NAME	COUNTRY
TAISHO PHARMACEUT CO LTD	N/A

APPL-NO: JP04294349

APPL-DATE: November 2, 1992

INT-CL (IPC): A61K009/70 , A61K009/70

**ABSTRACT:**

**PURPOSE:** To obtain a cross-linking type cataplasm base having high tack and high base strength in a high cross-linked state free from transfer of plaster to skin during peeling cataplasm.

**CONSTITUTION:** A cross-linking type cataplasm base consisting essentially of a polyacrylic acid and/or its salt is blended with ≤8wt.%, preferably 0.5-4wt.% silicic acid anhydride having preferably ≤50μ average particle diameter. The amount of the polyacrylic acid and/or its salt used in the base is 3-20wt.%. Aluminum hydroxide, magnesium metasilicate aluminate, aluminum magnesium hydroxide, synthetic hydrotalcite, etc., as a polyvalent metal salt is used as the cross-linking agent. Optionally a pH adjustor, a stabilizer, an antioxidant, a water-soluble polymer, a water retaining agent, etc.,

are further added to the cross-linking type cataplasma base. The cross-linking type cataplasma base has excellent balance of tack and strength of base and use of a tacky tape comprising an oily tacky agent or a fixing net which has been utilized in applying a cataplasma having weak tack to the affected part is not required.

COPYRIGHT: (C)1994,JPO&Japio